



## Viscous Control of the Foam Glass Process

Petersen, Rasmus Rosenlund; König, Jakob; Smedskjær, Morten Mattrup; Yue, Yuanzheng

*Publication date:*  
2014

*Document Version*  
Early version, also known as pre-print

[Link to publication from Aalborg University](#)

*Citation for published version (APA):*

Petersen, R. R., König, J., Smedskjær, M. M., & Yue, Y. (2014). *Viscous Control of the Foam Glass Process*. Abstract from 1st Joint Meeting of DGG – ACerS GOMD, Aachen, Germany.

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

### Take down policy

If you believe that this document breaches copyright please contact us at [vbn@aub.aau.dk](mailto:vbn@aub.aau.dk) providing details, and we will remove access to the work immediately and investigate your claim.

# Viscous Control of the Foam Glass Process

**Rasmus R. Petersen<sup>1,\*</sup>, Jakob König<sup>1,2</sup>, Morten M. Smedskjaer<sup>1</sup>, Yuanzheng Yue<sup>1</sup>**

<sup>1</sup> Section of Chemistry, Aalborg University, DK-9000 Aalborg, Denmark

<sup>2</sup> Advanced Materials Department, Jožef Stefan Institute, SI-1000 Ljubljana, Slovenia

\* Corresponding author. E-mail: [rp@bio.aau.dk](mailto:rp@bio.aau.dk)

The production of foam glass as heat insulating material is an important industrial process because it enables low-cost recycling of glass waste from a variety of chemical compositions. Optimization of the foaming process of new glass waste compositions is time consuming, since many factors affect the foaming process such as temperature, particle size, type and concentration of foaming agent. The foaming temperature is one of the key factors, because even small temperature changes can affect the melt viscosity by several orders of magnitude. Therefore, it is important to establish the viscosity range in which the foaming process should take place, particularly when the type of recycled cullet is changed or several types of cullet are mixed in one batch. According to recent glass literature, the foaming process should occur at viscosity  $10^3$  to  $10^5$  Pa s. However, no systematic studies have hitherto been conducted concerning how the melt rheology influences the foam glass process and if any universal optimum viscosity exist for foaming different types of glass cullet. In this work, we show the details of viscous control of glass foaming processes. We have measured the viscosity-temperature relationships for several types of glasses, and carried out the foam processes at different viscosities by using  $\text{CaCO}_3$  as foaming agent to find a common optimum viscosity for all the tested glasses. We also measured the particle size distribution of the recycled cullet, and quantified the degree of foam expansion through density measurements. The produced foam glasses have also been characterized in terms of the fraction of open vs. closed pores and crystallization and glass transition behaviour. Finally, we have found a minimum in the glass foam density when the foaming has been performed at viscosities of around  $10^4$  to  $10^5$  Pa s.